FT 0900X PET

Avery Dennison™ FT 0900X PET is a 36 mil single coated black flock with a high performance low VOC acrylic adhesive and a polyester release liner. The adhesive bonds very well to low surface energy materials and the flock provides anti-squeak properties with high wear resistance. FT 0900X PET is commonly used in automotive applications and where low VOC properties are required.

FEATURES

- Single coated tape construction
- · Low outgassing high performance modified acrylic adhesive
- Nylon flock facestock
- · Polyester film release liner



BENEFITS

- · Functional tape that allows for die cutting
- Solvent free adhesive with good adhesion to low surface energy materials
- Good heat resistance
- High abrasion resistance and NVH reduction
- Excellent moisture stability and die cutting properties with good converting performance
- Two-year warranty

CONSTRUCTION:

Liner:

2 mil Clear PET

Adhesive:

Low VOC Acrylic

Carrier:

Flock







FT 0900X PET

| Adhesive Properties: | | Typical Values | | |
|--|--------------|----------------|----------|---------------|
| Thickness | ASTM D3652 | US Mils | MM's | Micron's (µm) |
| Liner | | 2.0 | 0.05 | 51 |
| Adhesive | | 4.8 | 0.12 | 122 |
| Carrier | | 31.0 | 0.79 | 787 |
| | | | | |
| Total Caliper without Liner: | | 35.8 | 0.91 | 909 |
| Total Caliper: | | 37.8 | 0.96 | 960 |
| - I A II I | 40TM D0000 | | | |
| Peel Adhesion | ASTM D3330 | | | |
| 180° 12 in (300 mm) min @ R Substrate | Room Temp | Lbf / in | | N / Meter |
| SS | 72 hr dwell | 9.0 | <u> </u> | 1,585 |
| 33 | 72 III uweli | 9.0 | | 1,383 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| ABS | 72 hr dwell | 10.0 | | 1,761 |
| ADO | 72 III GWEII | 10.0 | | 1,101 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | l e | |
| Loop Tack | ASTM D6195 | | | |
| | Room Temp | | | |
| Substrate | • | Lbf / in | | N / Meter |
| SS | Initial | 3.5 | | 616 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| Static Shear | ASTM D3654 | | | |
| | ② Room Temp | | | |
| Substrate | | Min to Fail | , | |
| SS | 24 hr dwell | > 10,000 | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| TEMPERATURES | | ° F | , | ° C |
| Minimum Application Temperature | | 50° F | | 10° C |
| Minimum Service Temperature | | -40° F | | -40° C |
| Maximum Service Temperature | | 350° F | | 175° C |

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

• Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance Tapes Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

Phone: +86 512 57155001 Fax: +86 512 57155059 Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium Phone: +32 (0)14 40 48 11

Fax: +32 (0)14 40 48 55

North America 250 Chester Street Painesville, Ohio 44077 USA Phone: +1 866-462-8379

Fax: +1 888-358-4469

