



Authorized Distributor,
Converter, and Fabricator
www.jbc-tech.com

**Custom
Laminating**
Corporation

5243

FOIL / SCRIM / CO-POLYMER FILM

Tentative Specification

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
Foil	Aluminum	0.001 inch	25.4 microns
Reinforcement	Bi-directional 150/0 Fiberglass	5 / inch (MD) 5 / inch (XD)	20 / 100 mm (MD) 20 / 100 mm (XD)
Adhesive	Hi Temp Co-Polymer		
Film	Heat Seal Co-Polymer	0.00125 inch	31.8 microns

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	23.1 lbs / 1000 ft ²	113 g / m ²
Caliper / Thickness	Micrometer	0.0078 inch	198 microns
Mullen Burst	ASTM D774	90 psi	620 kPa
Tensile Strength	ASTM C1136	40 lbs / inch width (MD) 40 lbs / inch width (XD)	7.0 kN / m (MD) 7.0 kN / m (XD)
Low Temperature Resistance	ASTM C1263 -40°F (-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	10 minutes @ 401°F (205°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	48 hours @ 73°F (23°C)	No Delamination	No Delamination
Emissivity (Foil Side)	ASTM E408	≤ 0.05	≤ 0.05

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

Custom Laminating Corporation
5000 River Road · Mt. Bethel, PA 18343-5610
Ph: (570) 897 – 8300 · Fax (570) 897 – 6090

www.customl.com

August 2016

April 2015

Approval: FKB