

K-FONIK AB

OPEN CELL
NBR/PVC



Specification	Classification	Notes
UL 94	HF-1	Pass at 4.2mm (Listing in Progress)
UL 50 & 50E	--	Suitable for enclosure types 2, 3, 3R, 3S, 4, 4X, 5, 6, 6P, 12, 12K, and 13, including oil immersion (File #: JMST2.MH60641)



Authorized Distributor,
Converter, and Fabricator
www.jbc-tech.com

► K-FONIK AB

TECHNICAL DATA ►

Property	Value (K-FONIK AB 10)	Value (K-FONIK AB 15)	Test method
Polymer	NBR/PVC	NBR/PVC	
Cell structure	Open (Re-Bonded)	Open (Re-Bonded)	
Color	Primarily black	Primarily black	
Density	10 LB/FT ³	15 LB/FT ³	ASTM D1056
25% Compression Resistance	1.3-1.8 PSI Max	6.5-7.5 PSI Max	ASTM D1056
50% Compression Set	2% Max	8% Max	ASTM D1056
Tensile	7 PSI Min	10 PSI Min	ASTM D412 (DIE A)
Elongation	25% Min	25% Min	ASTM D412 (DIE A)
Flammability	Pass (Listing in Progress) Pass	Pass (Listing in Progress) Pass	UL 94 HF-1 FMVSS-302
Service temperature	-40°F to +185°F	-40°F to +185°F	
Thermal conductivity (75°F)	0.30 BTU-IN/HR-FT ² -°F	0.30 BTU-IN/HR-FT ² -°F	ASTM C177
Sound absorption	0.75 (1") NRC 0.85 (2") NRC	0.70 (1") NRC	ASTM C423
Sound blocking	9 RW (dB)	14 RW (dB)	UNI EN ISO 717-1 :2007
Air erosion	4,000 FPM Rating	4,000 FPM Rating	ASTM C1071

K-FLEX reserves the right to change data and technical requirements without notice.

RANGE ►

Size	Thickness*				Width		Length	
	Min (mm)	Max (mm)	Min (in)	Max (in)	Min (in)	Max (in)	Min (ft)	Max (ft)
1/2" **	12.7	15.3	0.500	0.602	59.0	60.0	79.0	80.0
1"	25.4	30.1	1.000	1.185	59.0	60.0	79.0	80.0
2"	50.8	55.9	2.000	2.201	59.0	60.0	79.0	80.0

Full buns are over 19" thick.

* Sheet Thickness should be checked using a calibrated caliper.

** AB 15 only.

US_LEA_K-TEK K-FONIK AB_1017



K-FLEX USA LLC 100 Nomaco Drive Youngsville, NC 27596
Phone: 800-765-6475
info@kflexusa.com
www.kflexperformancefoams.com