

August, 2016

3M™ Adhesive Transfer Tape 6035PC



Authorized Distributor,
Converter, and Fabricator
www.jbc-tech.com

Product Description

3M™ Acrylic Adhesive Transfer Tape 6035PC is a 5 mil transfer tape formulated for low fog characteristics. The 300MP adhesive is suitable for bonding to most substrates including foams, fabrics and substrates with rough or textured surfaces.



General Information

- 3M 6035PC meets automotive OEM fogging specifications
- Provides excellent bond to a wide variety of surfaces.
- High initial tack for quick and easy assembly line application.
- High temperature resistance to withstand environmental conditions normally associated with automotive interiors.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values	
Adhesive Type	#300MP Acrylic Adhesive	
Adhesive Thickness	0.127 mm	5 mil
Liner	58# Polycoated Kraft Paper	
Liner Thickness	0.107 mm	4.2 mil

Typical Performance Characteristics

Property	Values		Test Condition
Relative High Temperature Operating Ranges	121 °C	250 °F	Short Term (minutes, hours)
Flammability Test	Pass FMVSS 302/SAE J369		
Automotive Fogging Test	99		SAE J1756 @ 100°C

Environmental Performance (90° Peel)		Environmental Condition
7.1 N/cm	65 oz/in	Unleaded Gas at 1 Hour Room Temperature
4.3 N/cm	39 oz/in	MEK at 1 Hour Room Temperature
9.7 N/cm	89 oz/in	Weak Acid (pH 4) at 4 Hours Room Temperature
8.9 N/cm	81 oz/in	Weak Base (pH 10) at 4 Hours Room Temperature
12.4 N/cm	114 oz/in	Oil (10W30) at 72 Hours 120°F(49°C)
14.7 N/cm	134 oz/in	Water – 100 hours, Room Temperature
15.3 N/cm	140 oz/in	7 Days at 90°F(32°C) and 90% Relative Humidity
14.7 N/cm	134 oz/in	Temperature Cycling: 4 Hours at 158°F (70°C) 4 Hours at -20°F (-29°C) 16 Hours at Room Temperature Repeat three times

Table continued on next page

Typical Performance Characteristics (continued)

Environmental Performance (90° Peel)		Environmental Condition
12.4 N/cm	113 oz/in	Sodium Chloride Solution (5%) - 72 hrs. @ R.T
20.9 N/cm	191 oz/in	Ultraviolet Light - 30 days exposure

Property: Environmental Performance (90° Peel)

Dwell/Cure Time: 24 hr

Substrate: Stainless Steel

Backing: Aluminum Foil

notes: 12 inches/minute (305 mm/minute)

90° Peel Adhesion		Dwell/Cure Time	Substrate
11.2 N/cm	102 oz/in	15 min @ Room Temperature	Stainless Steel
14.3 N/cm	131 oz/in	72 hr @ Room Temperature	Stainless Steel
18.2 N/cm	166 oz/in	72 hr @ 158°F(70°C)	Stainless Steel
9.7 N/cm	89 oz/in	15 min @ Room Temperature	Polycarbonate (PC)
10.5 N/cm	96 oz/in	72 hr @ Room Temperature	Polycarbonate (PC)
7.3 N/cm	67 oz/in	72 hr @ 158°F(70°C)	Polycarbonate (PC)
8 N/cm	73 oz/in	72 hr @ Room Temperature	Polypropylene (PP)
6.9 N/cm	63 oz/in	72 hr @ 158°F(70°C)	Polypropylene (PP)
10 N/cm	93 oz/in	72 hr @ Room Temperature	ABS
8.5 N/cm	78 oz/in	72 hr @ 158°F(70°C)	ABS

Property: 90° Peel Adhesion

Method: ASTM D3330

Backing: 2 mil Aluminum Foil

notes: 12 in/min (300 mm/min)

Typical Environmental Performance

Property	Values
Humidity Resistance	No adverse effect on the bond after exposure to 100% relative humidity at 100°F (38°C)
U.V. Resistance	Adhesive is resistant to oxidation and ozone when exposed to air or ultraviolet light.
Bond Build-Up	The bond strength of the adhesive increases as a function of time and temperature.

Storage and Shelf Life

Product retains its performance properties for 24 months from date of manufacture if properly stored at room temperature conditions of 72°F (22°C) and 50% relative humidity.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M’s control and uniquely within user’s knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer’s application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M’s option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Trademarks

3M is a trademark of 3M Company.

References

Safety Data Sheet (SDS)

https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=6035PC

Family Group

	6035PC	6035PL	6038PC	6038PL
Relative High Temperature Operating Ranges (°C) Test Condition: Short Term (minutes, hours)	121	121	121	121
Adhesive Type	#300MP Acrylic Adhesive	#300MP Acrylic Adhesive	#300MP Acrylic Adhesive	#300MP Acrylic Adhesive
Adhesive Thickness (mm)	0.127	0.127	0.203	0.203
Liner	58# Polycoated Kraft Paper	83# Polycoated Kraft Paper	58# Polycoated Kraft Paper	83# Polycoated Kraft Paper
Liner Thickness (mm)	0.107	0.157	0.107	0.157

3M™ Adhesive Transfer Tape 6035PC

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.



Industrial Adhesives and Tapes Division
3M Center
St. Paul, MN 55144-1000
800-362-3550
www.3M.com

Please recycle.
© 3M 2019. All Rights Reserved.

The brands listed above are trademarks of 3M