



7887 Bliss Parkway, North Ridgeville, OH 44039
440.327.4522 www.jbc-tech.com

TECHNICAL DATA SHEET

5119 Aluminum Foil with Heat-Activated Co-Polymer Backing

COMPOSITION

		THICKNESS	
Foil	1100 Grade Aluminum	0.004 in (4 mil)	101.6 micron
Adhesive Film	High-Temperature Co-Polymer Heat Seal	0.00125 in (1.25 mil)	31.8 micron

PHYSICAL PROPERTIES*

	TEST METHOD	VALUE	
Basis Weight	Scale	62.7 lbs/1000 ft ²	306.8 g/m ²
Caliper/Thickness	Micrometer	0.0053 in (5.3 mil)	132.1 micron
Mullen Burst	ASTM D774	120 psi	827 kPa
Tensile Strength	ASTM C1136	35 lbs/inch width (MD) 35 lbs/inch width (MD)	6.1 kN/m (MD) 6.1 kN/m (XD)
Low Temperature Resistance	ASTM D1263 (-40°F/40°C)	Remains flexible No delamination	
High Temperature Resistance	10 minutes @ 401°F/205°C	Remains flexible No delamination	
Water Immersion	48 hours @ 73°F (23°C)	No delamination	

*Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

Disclaimer: Information contained in this data sheet is up-to-date and correct as at the date of issue. As JBC Technologies cannot control or anticipate the conditions under which this product may be used, each user should review the information in specific context of the planned use. To the maximum extent permitted by law, JBC Technologies will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given other than those implied mandatory by law.