



# FBR 8950 60#

Avery Dennison<sup>™</sup> FBR 8950 60# is a 4.0 mil double coated polyester with a general purpose rubber adhesive. It bonds well to polyurethane foams, fabrics and low surface energy materials. FBR 8950 60# is commonly used for foam bonding and general purpose attachment in automotive and appliance applications.

## FEATURES

- Double coated tape construction
- General purpose rubber adhesive
- · Polyester film carrier
- Super calendered kraft release liner

## BENEFITS

- Dimensional stability and good die cutting characteristics
- Strong bond to a wide variety of materials and good foam bonding performance
- High tensile strength and good converting performance
- High tensile strength and tear resistance with excellent die cutting performance
- Two-year warranty



# CONSTRUCTION:

Liner: 60# White Kraft Adhesive 1: Rubber Carrier: Polyester Adhesive 2: Rubber





Authorized Distributor, Converter, and Fabricator www.jbc-tech.com

### FBR 8950 60#

Adhesive Properties:	Typical Values			
Thickness	ASTM D3652	US Mils	MM's	Micron's (µm)
Liner		3.5	0.09	89
Adhesive 1 - Liner		1.4	0.04	36
Carrier		0.5	0.01	13
Adhesive 2 - Unwind		2.1	0.05	53
Total Caliper without Liner:		4.0	0.10	102
Total Caliper:		7.5	0.19	191

Teel Auliesion	ACTINI DOGGO		
180° 12 in (300 m	m) min   @ Room Temp		
Substrate		Lbf / in	N / Meter
SS	Liner 72 hr dwell	8.0	1,409
-			
	Unwind	8.5	1,497
		0.0	.,
PP	Liner 72 hr dwell	7.0	1,233
ГГ		1.0	1,235
-			
	11	0.5	4 407
	Unwind	8.5	1,497

Loop Tack	ASTM D6195			
180° 20 in (508 mm)	) / min @ Room Temp			
Substrate		Lbf / in	N / Meter	
SS	Liner Initial	10.0	1,761	
Static Shear	ASTM D3654			
180° 1" sq (6.5 cm2)	)1000 g @ Room Temp			
Substrate		Min to Fail		
SS	Liner 24 hr dwell	> 10,000		
TEMPERATURES		° F	° C	
Minimum Application Temperature		50° F	10° C	
Minimum Service Temperature		-40° F	-40° C	
Maximum Service Temperature		160° F	70° C	

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

## **APPLICATION TECHNIQUES**

It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil

• Bond strength is dependent upon the amount of adhesive-to-surface contact developed

Performance Tapes

· Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

#### STORAGE / SHELF LIFE

• Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335 Phone: +86 512 57155001 Fax: +86 512 57155059 Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 North America 250 Chester Street Painesville, Ohio 44077 USA Phone: +1 866-462-8379 Fax: +1 888-358-4469

