



7887 Bliss Parkway, North Ridgeville, OH 44039
440.327.4522 | www.jbc-tech.com

TECHNICAL DATA SHEET

5280 Aluminum Foil with Fiberglass Scrim & Heat-Activated Co-Polymer Backing

COMPOSITION

		THICKNESS	
Foil	1100 Grade Aluminum	0.002 in (2 mil)	50.8 micron
Reinforcement	Bi-directional Fiberglass	5/in (MD) 5/in (XD)	20/100 mm (MD) 20/100 mm (XD)
Adhesive Film	Co-Polymer Heat Seal	0.0009 in (0.9 mil)	22.9 micron

PHYSICAL PROPERTIES*

	TEST METHOD	VALUE	
Basis Weight	Scale	16.7 lbs/1,000 ft ²	81 g/m ²
Caliper/Thickness	Micrometer	0.0066 in (6.6 mil)	168 micron
Mullen Burst	ASTM D774	70 psi	482 kPa
Tensile Strength	ASTM C1136	33 lbs/inch width (MD) 33 lbs/inch width (MD)	5.8 kN/m (MD) 5.8 kN/m (XD)
Low Temperature Resistance	ASTM D1263 (-40°F/40°C)	Remains flexible No delamination	
High Temperature Resistance	10 minutes @ 401°F/205°C	Remains flexible No delamination	
Water Immersion	48 hours @ 73°F (23°C)	No delamination	
Emissivity (Foil Side)	ASTM E408	0.03	

*Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

Disclaimer: Information contained in this data sheet is up-to-date and correct as at the date of issue. As JBC Technologies cannot control or anticipate the conditions under which this product may be used, each user should review the information in specific context of the planned use. To the maximum extent permitted by law, JBC Technologies will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given other than those implied mandatory by law.