FT 8380

Avery Dennison™ FT 8380 was designed for use on bonding point-of-purchase display information to shelving materials.

FEATURES

- Specially formulated rubber based adhesive
- Polyester carrier
- · Densified kraft release liner

BENEFITS

- Clean removability from painted metal, glass and aluminum
- Excellent cold temperature performance



CONSTRUCTION:

Liner:

60# White Kraft

Adhesive 1:

Rubber

Carrier:

Polyester

Adhesive 2:

Rubber





Performance

FT 8380

F1 8380				
Adhesive Properties:	AOTH DOOS	110.14	Typical Values	
Thickness	ASTM D3652	US Mils	MM's	Micron's (µm)
Liner		3.5	0.09	89
Adhesive 1 - Liner		1.6	0.04	41
Carrier		0.5	0.01	13
Adhesive 2 - Unwind		1.2	0.03	30
Total Caliper without Line	er:	3.3	0.08	84
Total Caliper:		6.8	0.17	173
Peel Adhesion	ASTM D3330			
80° 12 in (305 mm) / m Substrate	nin	1 h £ / l m		N / Motor
	I to an install	Lbf / In 4.0	T	N / Meter 704
SS	Liner Initial	4.0		704
PP	Liner Initial	3.3	581	
		0.5		440
Painted Metal	Liner Initial	2.5		440
Aluminum	Liner Initial	2.9		511
	Linei	2.3		311
Glass	Liner Initial	3.8		669
	2			
Loop Tack	ASTM D6195		·	
180° 20 in (508 mm) / r				
ubstrate		Lbf / In		N / Meter
SS	Liner Initial	5.0		881
Unwind		18.8		3,311
Static Shear	ASTM D3654			
180° 1/2" sq (3.25 cm2)) 1000 g @ Room Temp	Mino 4- Fall		
Substrate	I in an Initial	Mins to Fail		
SS	Liner Initial	> 230		
TEMPERATURES		°F		° C
Minimum Application Temperature		20° F		-7° C
Maximum Continuous Operating Temperature		200° F		93° C
Maximum Intermittent Operating Temperature		225° F		105° C

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance



Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

Phone: +86 512 57155001 Fax: +86 512 57155059

Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55

North America 250 Chester Street Painesville, Ohio 44077 USA

Phone: +1 866-462-8379 Fax: +1 888-358-4469