

FBR 8950 12 Pt Board

Avery Dennison[™] FBR 8950 12 Pt Board is a 4.0 mil double coated polyester with a general purpose rubber adhesive and a heavy board release liner. It bonds well to polyurethane foams, fabrics and low surface energy materials. FBR 8950 12 Pt Board is commonly used for foam bonding and general purpose attachment in automotive and appliance applications.

FEATURES

- Double coated tape construction
- General purpose rubber adhesive
- · Polyester film carrier
- 12 point poly coated kraft board release liner

BENEFITS

- Dimensional stability and good die cutting characteristics
- Strong bond to a wide variety of materials and good foam bonding performance
- High tensile strength and good converting performance
- Heavyweight and stiffness allow for easy handling
- Two-year warranty



CONSTRUCTION:

Liner: Natural 12 Pt Board Adhesive 1: Rubber Carrier: Polyester Adhesive 2: Rubber



FBR 8950 12 Pt Board

FBR 8950 12 Pt Bo					
Adhesive Properties	1		Typical Values		
Thickness		ASTM D3652	US Mils	MM's	Micron's (µm)
Liner			12.9	0.33	328
Adhesive 1 - Liner			1.4	0.04	36
Carrier			0.5	0.01	13
Adhesive 2 - Unwind			2.1	0.05	53
Total Caliper without L	Liner:		4.0	0.10	102
Total Caliper:			16.9	0.43	429
Peel Adhesion		ASTM D3330			
180° 12 in (300 mm)	min @ Room Te				
Substrate		, in p	Lbf / in		N / Meter
SS	Liner 72 hr dwell		8.0		1,409
33	Linei		0.0		1,703
PP	Liner	72 hr dwell	7.0		1,233
Loop Tack		ASTM D6195			
180° 20 in (508 mm)	/ min @ Room				
Substrate		i onip	Lbf / in		N / Meter
SS	Liner	Initial	10.0		1,761
00	LING	initia	10.0		1,101
Static Shear	1000 - 0 5	ASTM D3654			
180° 1" sq (6.5 cm2)	1000 g @ Room	1 emp			
Substrate			Min to Fail		
SS	Liner	24 hr dwell	> 10,000		
TEMPERATURES			°F		° C
Minimum Application Temperature			50° F		10° C
Minimum Service Temperature			-40° F		-40° C
Maximum Service Temperature			160° F		70° C
					10 0

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

• It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil

• Bond strength is dependent upon the amount of adhesive-to-surface contact developed

· Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

• Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.





Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335 Phone: +86 512 57155001 Fax: +86 512 57155059 Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 North America 250 Chester Street Painesville, Ohio 44077 USA Phone: +1 866-462-8379 Fax: +1 888-358-4469