# FM 2108

Avery Dennison™ FM 2108 is a 130 mil double coated white polyethylene foam with a high shear rubber adhesive. It bonds to a wide variety of low surface energy materials and features high shear strength and the ability to fill gaps. FM 2108 is commonly used in general industrial foam applications.

#### **FEATURES**

- Double coated tape construction
- High shear rubber adhesive
- Polyethylene foam carrier
- · Super calendered kraft release liner



#### **BENEFITS**

- Dimensional stability and good die cutting characteristics
- Strong bond to a wide variety of low surface energy materials
- High shear and high temperature resistance
- Gap filling properties and good conformability
- High tensile strength and tear resistance with excellent die cutting performance
- Two-year warranty

# **CONSTRUCTION:**

Liner:

60# White Kraft

Adhesive 1:

Rubber

Carrier:

Polyethylene Foam

Adhesive 2:

Rubber







#### FM 2108

-M 2108 Adhesive Properties:		Typical Values			
Thickness	ASTM D3652	US Mils	MM's	Micron's (μm)	
Liner	AO 1 NI D3032	3.5	0.09	89	
Adhesive 1 - Liner		2.5	0.09	64	
Adnesive i - Liner Carrier		125.0	3.18	3175	
		2.5	0.06	64	
Adhesive 2 - Unwind		2.5	0.06	04	
Total Caliper without Li	ner:	130.0	3.30	3302	
Total Caliper:		133.5	3.39	3391	
i otai oanpoii					
Peel Adhesion	ASTM D3330				
180° 12 in (300 mm) r	nin @ Room Temp				
Substrate		Lbf / in		N / Meter	
SS	Liner 72 hr dwell	4.0		704	
	I berrie d	4.0		704	
	Unwind	4.0		704	
PP	Liner 72 hr dwell	4.0		704	
•	Later 12 th Gwell	4.0		107	
	Unwind	4.0		704	
				-	
				-	
L <b>oop Tack</b> 180° 32 in (508 mm) /	ASTM D6195 min @ Room Temp				
Substrate		Lbf / in		N / Meter	
SS	Liner Initial	6.5		1,145	
,,,	Lation initial	0.0		1,110	
	•	•	L		
Static Shear	ASTM D3654				
180° 1" sq (6.5 cm2)	1000 g @ Room Temp		-	-	
Substrate		Min to Fail			
SS	Liner 24 hr dwell	> 10,000			
				·	
		_			

## THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

# Maximum Service Temperature **APPLICATION TECHNIQUES**

Minimum Service Temperature

Minimum Application Temperature

**TEMPERATURES** 

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- · Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

### STORAGE / SHELF LIFE

• Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance

Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

Phone: +86 512 57155001 Fax: +86 512 57155059

Europe Tieblokkenlaan 1 B-2300 Turnhout Belaium Phone: +32 (0)14 40 48 11

50° F

-40° F

Fax: +32 (0)14 40 48 55

North America 250 Chester Street Painesville, Ohio 44077 USA Phone: +1 866-462-8379

Fax: +1 888-358-4469

° C

10° C

-40° C

80° C

