

3M™ Vibration Damping Tape 435

Last Revision Date: May, 2022

Product Description

3M[™] Vibration Damping Tapes are low temperature 3M[™] Viscoelastic Damping Polymers coated on a dead soft aluminum foil constraining layer. They have pressure sensitive properties and are furnished in roll form and designed for direct, pressure sensitive application to metal and composite panels for vibration damping purposes. The combination of the low temperature 3M viscoelastic polymers and an aluminum constraining layer has proven to be an unique construction with exceptional ability to damp resonant vibrations in the temperature range of -76° to +68°F (-60° to +20°C), with survivability from -76° to +248°F (-60° to +120°C).

Product Features

- Pressure sensitive construction for easy application.
- Excellent aging qualities of the 3M viscoelastic damping polymer type 830 provide long term performance and has excellent resistance to most hydrocarbon and/or aircraft type solvents.
- Wide temperature range for damping. Usable from -76° to 68°F (-60° to 120°C) at 100 Hz plus higher temperatures at higher frequencies.
- These linered products offer the user die-cut capability.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values	Additional Information
Backing	Dead Soft Aluminum Foil	
Liner	Polypropylene	
Liner Color	Blue	View ^
Test Name: Primary		
Damping Polymer Thickness	0.14 mm	
Backing Thickness	0.2 mm	

Total Tape Thickness	13.5 mil	View ^

Test Method: ASTM D3652

Total Tape Thickness	0.34 mm	View ^
Test Method: ASTM D3652		
Damping Polymer Thickness	5.5 mil	
Backing Thickness	8 mil	
Weight	0.675 g/m²	View ^
Test Method: ASTM D1000		
Weight	0.138 lb/in²	View ^
Test Method: ASTM D1000		
Water Vapor Transmission	0.4 - /400 1-2 /0.4 -	View ^
	0.1 g/100 in²/24 hr	VIEW
Tart Matheral ACTM DOOGO		
Test Method: ASTM D3833		
Test Method: ASTM D3833 Damping Polymer	Synthetic	
	Synthetic	
	Synthetic	
Damping Polymer		Additional Information
Damping Polymer Typical Performance Characteristics		Additional Information View ^
Damping Polymer Typical Performance Characteristics Property	Values	
Damping Polymer Typical Performance Characteristics Property Tensile Strength	Values	
Damping Polymer Typical Performance Characteristics Property Tensile Strength	Values	
Damping Polymer Typical Performance Characteristics Property Tensile Strength Test Method: ASTM D3759 Test Method: ASTM D3330	Values 147 N/cm	View ^
Damping Polymer Typical Performance Characteristics Property Tensile Strength Test Method: ASTM D3759 180° Peel Adhesion	Values 147 N/cm	View ^
Damping Polymer Typical Performance Characteristics Property Tensile Strength Test Method: ASTM D3759 Test Method: ASTM D3330	Values 147 N/cm	View ^
Damping Polymer Typical Performance Characteristics Property Tensile Strength Test Method: ASTM D3759 180° Peel Adhesion Test Method: ASTM D3330 Notes: 12 in/min (300 mm/min)	Values 147 N/cm 724 N/cm	View ^
Damping Polymer Typical Performance Characteristics Property Tensile Strength Test Method: ASTM D3759 180° Peel Adhesion Test Method: ASTM D3330 Notes: 12 in/min (300 mm/min) 180° Peel Adhesion	Values 147 N/cm 724 N/cm	View ^
Damping Polymer Typical Performance Characteristics Property Tensile Strength Test Method: ASTM D3759 180° Peel Adhesion Test Method: ASTM D3330 Notes: 12 in/min (300 mm/min) 180° Peel Adhesion Test Method: ASTM D3330	Values 147 N/cm 724 N/cm	View ^
Damping Polymer Typical Performance Characteristics Property Tensile Strength Test Method: ASTM D3759 180° Peel Adhesion Test Method: ASTM D3330 Notes: 12 in/min (300 mm/min) 180° Peel Adhesion Test Method: ASTM D3330 Notes: 12 in/min (300 mm/min)	Values 147 N/cm 724 N/cm 65 oz/in	View ^
Damping Polymer Typical Performance Characteristics Property Tensile Strength Test Method: ASTM D3759 180° Peel Adhesion Test Method: ASTM D3330 Notes: 12 in/min (300 mm/min) 180° Peel Adhesion Test Method: ASTM D3330 Notes: 12 in/min (300 mm/min) Tensile Strength	Values 147 N/cm 724 N/cm 65 oz/in	View ^

1:014	^
√iew	

Test Method: ASTM D3759

Minimum Long Term Temperature Resistance -60 °C	Long Term Temperature Resistance	120 °C		
Minimum Long Term Temperature Resistance -60 °C				
	Minimum Long Term Temperature Resistance	-60 °C		

Long Term Temperature Resistance	248 °F
Minimum Long Term Temperature Resistance	-76 °F

Flammability Test	Pass FAR 25.853(a)

Typical Damping Properties

Note Regarding Dynamic Mechanical Properties:

The shear storage modulus (G') and loss factor of a viscoelastic adhesive are two parameters used to partially define the damping performance when used in the form of a constrained layer damping treatment. The above curves illustrate these data as a function of frequency and temperature in the form of a reduced temperature nomograph. While the damping performance of a constrained layer damping treatment depends largely on the dynamic mechanical properties of the viscoelastic adhesive alone, it is also dependent on other parameters. Namely the geometry, stiffness, mass and mode shape of the combination of the damper and the structure to which it is applied will also affect the damping performance.

To determine the dynamic mechanical properties at the desired temperature and frequency proceed as follows:

- 1. Locate the desired frequency on the right vertical scale.
- 2. Follow the chosen frequency horizontally to the desired temperature isotherm.
- 3. From the intersect, move vertically up and/or down until crossing both the modulus and loss factor curves.
- 4. Read the shear storage modulus and loss factor values from the left vertical scale.

Storage and Shelf Life

Store under normal conditions of 60° to 80°F (16° to 27°C) and 40 to 60% R.H. in the original carton. To obtain best performance, use this product within 24 months from date of manufacture.

To obtain best performance, use this product within 24 months from date of manufacture

Ordering Information

To obtain best performance, use this product within 24 months from date of manufacture

Bottom Matter

3M Industrial Business Industrial Adhesives and Tapes Division 3M Center, Building 223-3S-06, St. Paul, MN 55144-1000

For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/industrialtape. Address correspondence to: 3M Industrial Adhesives and Tapes Division, Building 225-3S-06, St. Paul, MN 55144-1000. Our fax number is 877-369-2923. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

Automotive Disclaimer

Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, including, but not limited to, automotive electric powertrain battery or high voltage applications. This product does not fully adhere to typical automotive design or quality system requirements, such as IATF 16949 or VDA 6.3. This product may not be manufactured in an IATF certified facility and may not meet a Ppk of 1.33 for all properties. The product may not undergo an automotive production part approval process (PPAP). Customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's automotive application and for conducting incoming inspections before use of the product. Failure to do so may result in injury, death, and/or harm to property. No written or verbal statement, report, data or recommendation by 3M related to automotive use of the product shall have any force or effect unless in an agreement signed by the Technical Director of 3M's Automotive Division. Customer assumes all responsibility and risk if customer chooses to use this product in an automotive electric powertrain battery or high voltage application, and 3M will not be liable for any loss or damage arising from or related to the 3M product or customer's use of the product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity or recall costs), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability. In no event shall 3M be liable for any damages in excess of the purchase price paid for the product.

NOTWITHSTANDING ANY OTHER STATEMENT TO THE CONTRARY, 3M MAKES NO REPRESENTATIONS, WARRANTIES OR CONDITIONS WHATSOEVER, EXPRESS OR IMPLIED, REGARDING THE PRODUCT IF USED IN AN AUTOMOTIVE ELECTRIC POWERTRAIN BATTERY OR HIGH VOLTAGE APPLICATION, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY ON PERFORMANCE, LONGEVITY, SUITABILITY, COMPATIBILITY, OR INTEROPERABILITY, OR ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE.

Handling/Application Information

Application Examples

- For lower temperature aerospace and industrial applications.
- Reduce unwanted resonant noise, vibration and fatigue in metal panels and support structures.
- Chutes, conveyors, bins, metal shop boxes and tables where metal contact with materials can result in unwanted vibration.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/p/d/b40067969/
Safety Data Sheet SDS	https://www.3m.com/3M/en_US/company-us/SDS-search/results/? gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=435

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use.

Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.