


Double-Coated Closed Cell Foam Tape

3589A



Applications

- Electrodes: ECG, EKG, TENS
- Medical device assembly

• Medical device attachment

Features	Benefits
Polyethylene Foam Carrier	Soft and flexible for maximum patient comfort
	Conformable to adapt to medical devices and body contours
Non-Sensitizing Acrylic Adhesive	High tack and good shear for a variety of applicationsStable to EtO and gamma sterilization
60lb Release Liner	Easy to die-cut and convert

Typical Test Values

	Standard UOM	Metri	c UOM	Test Method PSTC 133
Total Thickness w/liner	68.5 mils	1.740	mm	
Adhesive Thickness (Air Side)	1.1 mils	0.028	mm	PSTC 133
Adhesive Thickness (Liner Side)	1.4 mils	0.036	mm	PSTC 133
Carrier Thickness	62.5 mils	1.588	mm	PSTC 133
Liner Thickness	3.5 mils	0.089	mm	PSTC 133
Adhesion to Steel (Air Side)	160 oz/in	17.50	N/cm	PSTC 101 Mod
Adhesion to Steel (Liner Side)	160 oz/in	17.50	N/cm	PSTC 101 Mod
	_			

Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-sensitizing, and non-irritating. The adhesive in this product has also been tested on humans via Repeat Insult Patch Test and did not induce irritation or allergic contact dermatitis in subjects.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the information and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

