



FM 2333


Avery Dennison™ FM 2333 is a 36 mil double coated white polyethylene foam with a modified acrylic adhesive. It bonds well to low surface energy materials and has the ability to fill gaps. FM 2333 is commonly used in general industrial foam applications.

FEATURES

- Double coated tape construction
- Modified acrylic adhesive for low surface energy substrates
- Polyethylene foam carrier
- Super calendered kraft release liner

BENEFITS

- Dimensional stability and good die cutting characteristics
- Strong bond to low surface energy materials
- Good heat resistance
- Gap filling properties and good conformability
- High tensile strength and tear resistance with excellent die cutting performance
- Two-year warranty



CONSTRUCTION:

Liner:

60# White Kraft

Adhesive 1:

Acrylic

Carrier:

Polyethylene Foam

Adhesive 2:

Acrylic

FM 2333

Adhesive Properties:		Typical Values		
Thickness	ASTM D3652	US Mils	MM's	Micron's (µm)
Liner		3.5	0.09	89
Adhesive 1 - Liner		2.3	0.06	58
Carrier		31.0	0.79	787
Adhesive 2 - Unwind		2.3	0.06	58
Total Caliper without Liner:		35.6	0.90	904
Total Caliper:		39.1	0.99	993

Peel Adhesion		ASTM D3330		
180° 12 in (300 mm) min @ Room Temp				
Substrate			Lbf / in	N / Meter
SS	Liner	72 hr dwell	8.5	1,497
	Unwind		8.5	1,497
ABS	Liner	72 hr dwell	5.5	969
	Unwind		5.5	969

Loop Tack		ASTM D6195		
180° 32 in (508 mm) / min @ Room Temp				
Substrate			Lbf / in	N / Meter
SS	Liner	Initial	9.0	1,585

Static Shear		ASTM D3654		
180° 1" sq (6.5 cm2) 1000 g @ Room Temp				
Substrate			Min to Fail	
SS	Liner	24 hr dwell	> 10,000	

TEMPERATURES	° F	° C
Minimum Application Temperature	50° F	10° C
Minimum Service Temperature	-40° F	-40° C
Maximum Service Temperature	225° F	105° C

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

- Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes.AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance
Tapes



Authorized
Converter &
Fabricator
www.jbc-tech.com

Asia Pacific
Kunshan, China,
NO. 618 Nanhe Road
Kunshan Economic &
Technological Zone
China, 215335
Phone: +86 512 57155001
Fax: +86 512 57155059

Europe
Tieblokkenlaan 1
B-2300 Turnhout
Belgium
Phone: +32 (0)14 40 48 11
Fax: +32 (0)14 40 48 55

North America
250 Chester Street
Painesville, Ohio
44077 USA
Phone: +1 866-462-8379
Fax: +1 888-358-4469