

F-20

Silicone Foam Rubber

Saint-Gobain® Norseal® F-20 is manufactured by **Saint-Gobain** Performance Plastics Corporation, Tape Solutions business, and comes with a medium density closed-cell silicone foam rubber product intended to deliver environmentally stable, flame-retardant performance for gasketing, insulation and dampening applications.

Norseal F-20 offers excellent compression set resistance and is often the product of choice in aircraft, aerospace, mass transit, military and electronic applications with extremely stringent smoke, flame and toxicity requirements. F-20 offers excellent resistance to environmental conditions, making it an excellent choice for both indoor and outdoor sealing and gasketing applications.

Norseal F-20 is specially intended to provide the following features:

- Meets key industry standards: FAR 25.853, Bombardier SMP 800-C, NFPA 130, UL V-0
- Recognized to UL 50E gasket and seals for electrical enclosures
- Non-toxic, low smoke generation and low flame spread
- Smooth surface on both sides for excellent sealing against air, dust, light and moisture
- Excellent compression set resistance
- Excellent resistance to ultraviolet light, ozone and extreme temperature ranges
- Meets requirements of FDA extractables 21.CFR177.2600 for food contact
- Closed-cell foam meets AMS 3195
- Non-corrosive for use with metals and in hostile environments
- Available as a pressure-sensitive adhesive tape under the **Norseal** Silicone SNS 520AF product line

Available Sizes

Standard thickness: .031, .063, .125, .188, .25, .375 and .50 in. (0.8, 1.6, 3.2, 4.8, 6.4, 9.6 and 12.7 mm)

Master roll size: 36 in. (914 mm) width. Length varies with thickness.

Special thickness and roll sizes also available.



APPLICATIONS

- Trains
- Medical equipment
- Aerospace
- Street lamps

Norseal F-20 — Properties

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

Property	Unit of Measure	Value	Test Method
Physical			
Colors	-	Gray	-
Tensile Strength	psi (kPa)	30 (207)	ASTM D412
Elongation at Break	%	60	ASTM D412
Density	lbs./ft ³ (kg/m ³)	20 (320)	ASTM D3574
Compression Deflection	psi (kPa)	8 (55.2)	ASTM D1056
Compression Set (50% for 22 hrs. at 212°F)	%	< 5	ASTM D1056
Surface Description	-	Smooth both sides	-
Flammability			
Flame Resistance (UL)	-	Pass	UL 94 V-0
Flame Resistance (FAR)	-	Pass	FAR 25.853 (12s & 60s)
Flame Spread Index	L ₁	< 35	ASTM E162
Smoke Density	D ₂	1.5 minutes < 20 4.0 minutes < 50	ASTM E662
Toxic Gas Emissions Rating	-	Pass	SMP-800C
Flame Propagation	-	Pass	ASTM C1166
Environmental			
Stain Resistance	-	Pass	ASTM D925 - 06e2, Method A
Ozone Effect Rating	-	No cracking	ASTM D1171-99 (2007), Method A
UV Resistance	Visual	No degradation	SAE J1960
Water Absorption	%	< 5	ASTM D471
Temperature Range	°F (°C)	-60 to + 400 (-51 to +204)	-
FDA Extractables	-	Pass	21 CFR 177.2600 (food contact)
Gasket and Seals for Electronic Enclosures	-	Pass	UL 50E
Electrical and Thermal			
Dielectric Strength	volts/mil (VPM)	80	ASTM D149
Dielectric Constant	-	3.5	ASTM 150
Dissipative Factor	-	0.03	ASTM 150
Dry Arc Resistance	Seconds	127	ASTM D495
Volume Resistivity	ohms-cm	3.39 × 10 ¹⁴	ASTM 257
Thermal Conductivity	W/m ² K	0.074	ASTM C518
Thermal Insulation (R-value)	ft. ² • h • °F/Btu • in	1.94	ASTM C518
Low Temperature Embrittlement	°F (°C)	-148 (-100)	DMA

Important Instructions

Because **Saint-Gobain** cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use.

Shelf Life

120 months from date of shipment for base material when stored in original packaging at temperatures up to 70°F (21°C), < 50% relative humidity, and away from direct sources of heat and direct sunlight. (See the applicable data sheets for pressure sensitive adhesive options).

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to your actions or inactions, including your use, design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: This document should not be considered a warranty or a guarantee. The descriptions of the Product provided hereinabove may vary based on specifications requested and testing protocols. Typically, Saint-Gobain warrants that product(s) will meet mutually agreed specifications at delivery and Saint-Gobain honors any breach of warranty claims for six (6) months from delivery of the products. If a product is determined to be nonconforming with its warranty, Saint-Gobain's sole obligation is, at its option, to either replace the nonconforming products or reimburse the purchase price for the same.

The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR USE.

Form #1331 | © Saint-Gobain April 2025 | All the mentioned trademarks are registered trademarks of Saint-Gobain Tape Solutions or affiliates, part of Saint-Gobain group.



TAPE SOLUTIONS

North America | South America
Europe | Asia

For more information, please visit
tapesolutions.saint-gobain.com