



3M™ High Strength Double Coated Tape 93010LE

Last Revision Date: May, 2022

Product Description

Finite Element Analysis (FEA) data is available for this product at: [3m.com/FEA](https://www.3m.com/FEA)

3M™ Double Coated Tapes with 3M™ High Strength Acrylic Adhesive 300LSE provides a high bond strength to most surfaces, including many low surface energy plastics such as polypropylene and powder coated paints. The acrylic adhesive also provides excellent adhesion to surfaces contaminated with oil typically used with machine parts.

Product Features








- This tape has a film carrier which can add dimensional stability to foams and other substrates and also makes it easier to handle the tape during slitting and die-cutting.
- The bond strength of 3M™ Acrylic Adhesive 300LSE increases as a function of time and temperature, and has very high initial adhesion.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.






Typical Physical Properties

Property	Values	Additional Information
Adhesive Type	Acrylic	
Adhesive Type	300LSE	View
Test Name: Faceside		
Notes: Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.		
Adhesive Type	300LSE	View
Test Name: Backside		
Notes: Backside adhesive is on the exterior of the roll, exposed when liner is removed.		
Adhesive Carrier	Clear Polyester	
Liner	58# Polycoated Kraft	
Liner Thickness	0.1 mm	

Liner Color	Tan	View 
Test Name: Primary		
Adhesive Thickness	0.044 mm	View 
Test Name: Backside		
Notes: The caliper listed is based on a calculation from manufacturing controlled adhesive coat weight. While past data pages have listed nominal thicknesses of 1 and 2 mils, the coat weight (and theoretical caliper) has not changed.		
Carrier Thickness	0.012 mm	
Total Tape Thickness	3.9 mil	View 
Test Method: ASTM D3652		
Total Tape Thickness	0.1 mm	View 
Test Method: ASTM D3652		
Adhesive Thickness	1.7 mil	View 
Test Name: Backside		
Notes: Backside adhesive is on the exterior of the roll, exposed when liner is removed.		
Adhesive Thickness	0.044 mm	View 
Test Name: Faceside		
Notes: Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.		
Adhesive Thickness	1.7 mil	View 
Test Name: Faceside		
Notes: Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.		
Carrier Thickness	0.5 mil	
Liner Print	300LSE	
Liner Thickness	4 mil	

Typical Performance Characteristics

Property	Values	Additional Information
Short Term Temperature Resistance	300 °F	

Short Term Temperature Resistance	149 °C	
Long Term Temperature Resistance	93 °C	
Long Term Temperature Resistance	200 °F	
Static Shear	>10,000 min	View 
<p>Test Method: ASTM D3654</p> <p>Notes: 1 in² sample size</p>		
Static Shear	>10,000 min	View 
<p>Test Method: ASTM D3654</p> <p>Notes: 1 in² sample size</p>		
180° Peel Adhesion	9.3 N/cm	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 15.0 Dwell Time Units: min Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Stainless Steel Backing: Aluminum Foil</p> <p>Notes: 12 in/min (300 mm/min)</p>		
180° Peel Adhesion	85 oz/in	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 15.0 Dwell Time Units: min Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Stainless Steel Backing: Aluminum Foil</p> <p>Notes: 12 in/min (300 mm/min)</p>		
180° Peel Adhesion	12.3 N/cm	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 15.0 Dwell Time Units: min Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Polycarbonate (PC) Backing: Aluminum Foil</p> <p>Notes: 12 in/min (300 mm/min)</p>		
180° Peel Adhesion	110 oz/in	

[View](#) 


Test Method: ASTM D3330

Dwell/Cure Time: 15.0
 Dwell Time Units: min
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Polycarbonate (PC)
 Backing: Aluminum Foil

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

8.8 N/cm

[View](#) 

Test Method: ASTM D3330

Dwell/Cure Time: 15.0
 Dwell Time Units: min
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: ABS
 Backing: Aluminum Foil

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

80 oz/in

[View](#) 

Test Method: ASTM D3330

Dwell/Cure Time: 15.0
 Dwell Time Units: min
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: ABS
 Backing: Aluminum Foil

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

10.4 N/cm

[View](#) 

Test Method: ASTM D3330

Dwell/Cure Time: 15.0
 Dwell Time Units: min
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Polypropylene (PP)
 Backing: Aluminum Foil

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

95 oz/in

[View](#) 

Test Method: ASTM D3330

Dwell/Cure Time: 15.0
 Dwell Time Units: min
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Polypropylene (PP)
 Backing: Aluminum Foil

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

12 N/cm

[View](#) 


Test Method: ASTM D3330

Dwell/Cure Time: 72.0
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Stainless Steel
 Backing: Aluminum Foil

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

110 oz/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Stainless Steel
 Backing: Aluminum Foil

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

15.3 N/cm

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Polycarbonate (PC)
 Backing: Aluminum Foil

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

140 oz/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Polycarbonate (PC)
 Backing: Aluminum Foil

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

12 N/cm

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: ABS
 Backing: Aluminum Foil

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

110 oz/in


View 


Test Method: ASTM D3330

Dwell/Cure Time: 72.0
 Dwell Time Units: hr
 Temp C: 23C






Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: ABS
 Backing: Aluminum Foil




Notes: 12 in/min (300 mm/min)

180° Peel Adhesion	12 N/cm	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Polypropylene (PP) Backing: Aluminum Foil</p> <p>Notes: 12 in/min (300 mm/min)</p>		

180° Peel Adhesion	110 oz/in	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Polypropylene (PP) Backing: Aluminum Foil</p> <p>Notes: 12 in/min (300 mm/min)</p>		

Available Sizes

Property	Values	Additional Information
Note	Subject to Minimum Order Requirements	
Maximum Length	164 m	View 
Width: 1/2 in to 63/64 in		
Maximum Length	180 yd	View 
Width: 1/2 in to 63/64 in		
Maximum Length	329 m	View 
Width: 1 in to 3 in		
Maximum Length	360 yd	View 
Width: 1 in to 3 in		
Maximum Length	329 m	View 
Width: 3 in to 48 in		

Maximum Length	360 yd	View 
Width: 3 in to 48 in		
Maximum Length	329 m	View 
Width: 48 in to 54 in		
Maximum Length	360 yd	View 
Width: 48 in to 54 in		
Normal Slitting Tolerance	± 0.8 mm	
Normal Slitting Tolerance	± 1/32 in	
Core Size (ID)	76.2 mm	
Core Size (ID)	3 in	

Electrical and Thermal Properties

Property	Values	Additional Information
Breakdown Voltage	5600 V	

Typical Environmental Performance

Humidity Resistance: High humidity has minimal effect on adhesive performance. No significant reduction in bond strength is observed after exposure for 7 days at 90°F (32°C) and 90% relative humidity.

UV Resistance: When properly applied, nameplates and decorative trim parts are not adversely affected by exposure.

Water Resistance: Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength is maintained.

Temperature Cycling Resistance: High bond strength is maintained after cycling four times through:

4 hours at 158°F (70°C)

4 hours at -20°F (-29°C)

4 hours at 73°F (22°C)

Chemical Resistance: When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids, and alkalis.

Storage and Shelf Life

Store in original cartons at 70°F (21°C) and 50% relative humidity.

If stored under proper conditions, these products retain their performance and properties for 24 months from date of manufacture.

Bottom Matter

3M

Industrial Adhesives and Tapes Division Converter Markets

3M Center, Building 225-3S-06 St. Paul, MN 55144-1000

800-223-7427 • 651-778-4244 (fax)

www.3M.com

Trademarks

3M is a trademark of 3M Company.

Automotive Disclaimer

Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, including, but not limited to, automotive electric powertrain battery or high voltage applications. This product does not fully adhere to typical automotive design or quality system requirements, such as IATF 16949 or VDA 6.3. This product may not be manufactured in an IATF certified facility and may not meet a Ppk of 1.33 for all properties. The product may not undergo an automotive production part approval process (PPAP). Customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's automotive application and for conducting incoming inspections before use of the product. Failure to do so may result in injury, death, and/or harm to property. No written or verbal statement, report, data or recommendation by 3M related to automotive use of the product shall have any force or effect unless in an agreement signed by the Technical Director of 3M's Automotive Division. Customer assumes all responsibility and risk if customer chooses to use this product in an automotive electric powertrain battery or high voltage application, and 3M will not be liable for any loss or damage arising from or related to the 3M product or customer's use of the product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity or recall costs), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability. In no event shall 3M be liable for any damages in excess of the purchase price paid for the product.

NOTWITHSTANDING ANY OTHER STATEMENT TO THE CONTRARY, 3M MAKES NO REPRESENTATIONS, WARRANTIES OR CONDITIONS WHATSOEVER, EXPRESS OR IMPLIED, REGARDING THE PRODUCT IF USED IN AN AUTOMOTIVE ELECTRIC POWERTRAIN BATTERY OR HIGH VOLTAGE APPLICATION, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY ON PERFORMANCE, LONGEVITY, SUITABILITY, COMPATIBILITY, OR INTEROPERABILITY, OR ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE.

Handling/Application Information

Application Examples

- Foam to powder coated painted surfaces.
- Low surface energy plastic adhesion.

Application Techniques

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improve bond strength. To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.*

*Note: Carefully read and follow the manufacturer's precautions and directions for use when using solvents. Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/p/d/b40070398/
Safety Data Sheet SDS	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=93010LE

Family Group

Link Tags:

- [93010LE](#)
- [93015LE](#)
- [93020LE](#)

Products	Adhesive Type	Adhesive Carrier	Liner	Liner Thickness	Liner Color	Adhesive Thickness	Carrier Thickness	Total Tape Thickness	Short Term Temperature Resistance	Long Term Temperature Resistance
----------	---------------	------------------	-------	-----------------	-------------	--------------------	-------------------	----------------------	-----------------------------------	----------------------------------

93015LE	300LSE	Clear Polyester	58# Polycoated Kraft	0.11 mm	Tan	0.069 mm	0.012 mm	0.15 mm	149 °C	200 °F
93010LE	300LSE	Clear Polyester	58# Polycoated Kraft	0.1 mm	Tan	0.044 mm	0.012 mm	0.1 mm	149 °C	200 °F
93020LE	300LSE	Clear Polyester	58# Polycoated Kraft	0.11 mm	Tan	0.095 mm	0.012 mm	0.2 mm	149 °C	200 °F

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.