# FASSON® 0817

Avery Dennison™ FASSON® 0817 is suitable for die-cut shapes, shielding, moisture and vapor barrier sealing components or lamination to insulation materials.

## **FEATURES**

- Dead-soft 2 mil foil facestock
- · Quick stick, cold-temperature rubber adhesive
- · Strong bleached densified kraft liner



# **BENEFITS**

- Strong bond to a variety of substrates
- · Conformability to curved surfaces
- Exceptional cold environment adhesion conditions
- Tested in accordance with UL 723
- Made in the USA

# **CONSTRUCTION:**

Liner:

50# White Kraft

Adhesive:

Rubber

Carrier:

Aluminum Foil



General Use Tape Surface Burning Characteristcs to

UL 723 Flame Spread 10

722S Smoke Developed 15







# FASSON® 0817 Adhesive Properties: Typical Values Thickness ASTM D3652 US Mils MM's Micron's Liner 3.2 0.08 81

Thickness	ASTM D3652	US Mils	MM's	Micron's (µm)
Liner		3.2	0.08	81
Adhesive		2.0	0.05	51
Carrier		2.0	0.05	51
Total Caliper without Liner:		4.0	0.10	102
Total Caliper:		7.2	0.18	183

Peel Adhesion	ASTM D3330		
180° 12 in (300 mm) min @	Room Temp		
Substrate		Lbf / in	N / Meter
SS	Initial	4.9	863

Loop Tack	ASTM D6195		
180° 20 in (508 mm) / min	@ Room Temp		
Substrate		Lbf / in	N / Meter
SS	Initial	12.0	2,113

Static Shear	ASTM D3654			
180° 1" sq (6.5 cm2)	1000 g @ Room Temp			
Substrate		Min to Fail		
SS	Initial	> 10,000		

TEMPERATURES	° F	° C
Minimum Application Temperature	50° F	10° C
Maximum Continuous Operating Temperature	175° F	79° C
Maximum Intermittent Operating Temperature	200° F	95° C

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

## **APPLICATION TECHNIQUES**

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- · Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

#### STORAGE / SHELF LIFE

One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance Tapes



Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

China, 215335 Phone: +86 512 57155001 Fax: +86 512 57155059 Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 North America 250 Chester Street Painesville, Ohio 44077 USA Phone: +1 866-462-8379

Fax: +1 888-358-4469